



Request No. 1477/670228

TPC. No. 1477/67

## REPORT ON TESTING AND ANALYSIS

For

PREPACK THAILAND CO., LTD.

30/145 Moo 1, Khok Kham, Muang Samutsakhon, Samutsakhon 74000

Testing/analysis of:- Plastic film; code: OPP/MCPP

Method of testing/analysis:- 1) ASTM F 1249-20 Water Vapor Transmission Rate Through Plastics Film and Sheeting Using a Modulated Infrared Sensor  
2) ASTM D 3985-17 Oxygen Gas Transmission Rate Through Plastic Film and Sheeting Using a Coulometric Sensor

Condition of testing/analysis:- Temperature - °C Relative humidity - %

Date of request:- February 28, 2024

Date of testing:- March 18-27, 2024

Result of testing/analysis:-

Water vapor transmission rate	0.133	g/m <sup>2</sup> .day
at 37.8 °C , 90.0 % RH		
Oxygen gas transmission rate	5.44	cc/ m <sup>2</sup> .day
at 23.0 °C , 0 % RH		

Note: 1) Water vapor transmission rate test:

- Test equipment: Water vapor permeation tester; MOCON PERMATRAN-W<sup>®</sup>3/34(G)

2) Oxygen gas transmission rate test:

- Test equipment: Oxygen permeation tester; Illinois model 8101e

Tested/analysed by

*Gansuda*

(Miss Gansuda Wangchanachai)

Approved by

*Wichit R.*

(Mr. Wichit Rattanathawornkiti)

Director of Packaging Testing Laboratory

Date April 5, 2024

# # End of Report # #

Remark: The above results are valid exclusively for tested/analyzed samples as mentioned in this report.  
Publicity and reproduce some parts are prohibited unless written permission is obtained from TISTR.

FS-PKL-SP-17025-04 Issue No.3

### Thailand Institute of Scientific and Technological Research

Head Office

35 Moo 3, Technopolis, Tambon Khlong 5, Amphoe Khlong Luang,  
Pathum Thani 12120,Thailand  
Tel. (662) 577 9000 Fax. (662) 577 9009  
E-mail: tistr@tistr.or.th Website : www.tistr.or.th

Thai Packaging Centre

196 Phahonyothin Road, Chatuchak,  
Bangkok 10900, Thailand  
Tel. (662) 579 1121-30 Fax. (662) 579 7573  
E-mail: tpc-tistr@tistr.or.th Website : www.tistr.or.th/tpc